

FENIX NTA® is a material produced by simultaneous application of heat and pressure, in order to obtain a homogeneous non-porous high density product. The core structure is composed of paper, impregnated with thermosetting resins. The outer surface is made of a real metal structure substrate treated with next generation acrylic resins applied to the substrate as a multilayer coating and subsequently, cured via an electron beam process.

fenixforinteriors.com Rev03-E-30-04-2020

				0.7 mm 1.2 mm MATCHED COLOUR CORE 1
PROPERTIES	TEST METHOD	PROPERTY OR ATTRIBUTE	UNIT	VALUES
		GENERAL PROPERTIES		
c f liv	EN 420 0 0040 1.4	Spots, dirt and similar surface defects	mm²/m²	≤ 1
Surface quality	EN 438-2:2019 cl.4	Fibres, hair and scratches	mm/m²	≤ 10
Dimensional tolerances	EN 438-2:2019 cl.5	Thickness tolerance	mm	0.7 ± 0.15 1.2 ± 0.18
	EN 438-2:2019 cl.6	Length and width	mm	+ 10 / - 0
	EN 438-2:2019 cl.7	Straightness of edges	mm/m	≤ 1.5
	EN 438-2:2019 cl.8	Squareness	mm/m	≤ 1.5
	EN 438-2:2019 cl.9	Flatness (measured on full-size sheet)	mm/m	≤ 100
		SURFACE PROPERTIES		
Resistance to surface wear	EN 438-2:2019 cl.10	Initial Point	Revolutions	≥ 200
Resistance to water vapour	EN 438-2:2019 cl.14	Appearance	Rating	5
Resistance to dry heat (160 °C/20')	EN 438-2:2019 cl.16	Appearance	Rating	5
Resistance to wet heat (100 °C/20')	EN 438-2:2019 cl.18	Appearance	Rating	5 n.a.
Resistance to scratching	EN 438-2:2019 cl.25	Appearance	Rating	≥ 4
Resistance to staining	EN 438-2:2019 cl.26	Appearance - Groups 1 and 2	Rating	5
		Appearance - Group 3	Rating	≥ 4
Light fastness (Xenon-arc)	EN 438-2:2019 cl.27	Contrast	Grey scale rating	≥ 4
Surface specular reflectance	ISO 2813	Surface specular reflectance	Gloss unit	8 ÷ 16 at 85°
Acids resistance	SEFA 8-PL-2010 Method 8.1	Chemical Spot Test	Suitability	Compliant
		PHYSICAL PROPERTIES		
Density	EN ISO 1183	Density	g/cm ³	≥ 1.35
Resistance to immersion in boiling water	EN 438-2:2019 cl.12	Appearance	Core delamination Pass or fail	Pass
Dimensional stability at high temperatures	EN 438-2:2019 cl.17	Cumulative dimensional change	Longitudinal %	≤ 0.75
Differsional stability at high temperatures	214 100 2:2017 6::17	Cumulative dimensional change	Transversal %	≤ 1.25
Resistance to cracking	EN 438-2:2019 cl.23	Appearance	Rating	≥ 4
		OTHER PROPERTIES		
		IVIRONMENTAL PROPERTIES		
Formaldehyde emission	EN 13986	Formaldehyde emissions	Rating	E1
Volatile Organic Chemical emissions	Greenguard Gold Certification Low Chemical Emission UL 2818	Volatile Organic Chemical emissions	Suitability	Greenguard Gold certified
	FOC	DD AND HYGIENE PROPERTIES		
Hygiene	NSF/ANSI 35	Suitability for use as work and nonwork surfaces of food service equipment on which direct food contact during normal preparation or holding operations is not intended, expected, or reasonable	Suitability	NSF certified
Food contact	Regulation EU n° 10/2011 and following amendments	Food Contact Materials performance	Suitability	Compliant - conditions of use reported in the Declaration of conformity

For the current and up to date FENIX® delivery program in North America, visit www.fenixforinteriors-na.com. For the delivery program in the rest of the world, visit www.fenixforinteriors.com. Please contact your sales representative for more information.

Note to FENIX sheets with adhesive protective film
The protective film is designed to temporary protect the surface from dust, scratches and marks left by handling equipment; it does not protect from corrosion, dampness or chemical agents.
Sheets covered with protective film should be stored in a clean dry atmosphere at room temperature (ideally 20 °C), avoiding exposure to atmospheric agents and UVA rays.
The protective film should be removed from the sheets surface after application and before the final item case of thick sheets with protective film on both sides, the film should always be removed from both sides at the same time. In any case, the removal should take place within 6 months from the date of shipping by the Manufacturer(s) of the FENIX sheets. The Manufacturer(s) of the FENIX sheets shall not accept liability for improper use of sheets covered with a protective film, nor for any consequences of an incorrect application.

Sheets Covered with a protective mining, not any growing and the performance of the product as tested by the Manufacturer(s) of FENIX sheets or certified testing body.

Any information contained within this document must be verified and tested for suitability by the user for his or her particular purpose or specific application. Consideration needs to be given to local or specific circumstances. The content of this document reflects our knowledge and experience at the time of publication. The newest version of the document replaces all previous versions. We advise that the newest version may contain technical changes that must be taken into account when using the products. The latest version of the document may be consulted on our website www.fenixforinteriors.com. Customers should always check whether an updated version of the document, but it cannot be held liable for any oversights, inaccuracies or typographical errors. The Manufacturer(s) of IECENIX sheets will not assume any liability if the end-user or customer refer to any other technical information of the products.